

# Technical Data Sheet



## Ressi CFM 920 2K

Two Component High strength Waterproof  
crack filling mortar

Ressi CFM 920 2K is a high quality two component filler material for the filling of static cracks, holes and levelling uneven surfaces on concrete and plaster.

### Advantages

- ✓ Fast and easy to use (mix and apply) only the addition of water is required
- ✓ Suitable for dry and wet areas internally and externally
- ✓ Excellent bonding, Crack Free
- ✓ Call fill cracks up to 50mm and easily coatable over hairline cracks
- ✓ Waterproof
- ✓ High strength

### Technical Data

Component	Two: Part A Liquid Polymer Part B White filling powder
Composition	Contains cement and selected aggregates along with additives to improved consistency, workability and durability
Maximum aggregate size	0.3mm
* Wet Mix life	Approximately 30 Mins (Tested as per BS EN 1015-9)
*Compressive Strength	8.00 N / mm <sup>2</sup> @ 28 Days (Tested as per BS EN 1015-11)
*Flexural Strength	3.00 N / mm <sup>2</sup> @ 28 Days (Tested as per BS EN 1015-12)
*Approximate Yield / Coverage	0.75 m <sup>3</sup> / T

\*Typical Results under laboratory conditions

**RESSICHEM** | ریسیکیم  
adding life and value to your property | مضبوطی اور پائیداری کے لئے

RESSICHEM (Pvt.) LIMITED

Plot # D-883, SITEE, Industrial Area, Mangalagiri Road, Kharcothi-755530, Rajasthan.  
Tel: +922 22133 2359 38800-02, Fax: +922 22133 2359 38803

[www.ressichem.com](http://www.ressichem.com)

# Technical Data Sheet



## **Ressi CFM 920 2K**

**Two Component High strength Waterproof  
crack filling mortar**

### Application

Remove dust, oil, grease, loose material and paints which may affect adhesion with the substrate. Moisten the surface with clean water before application. Put appropriate amount of clean water in a suitable pot or mixing container along with the appropriate amount of polymer Liquid. Add the required amount of **Ressi CFM 920 2K** powder gradually and mix for 3 minutes using a mechanical mixer till the mixture is uniform and free of lumps. Let the composition stand for about 3 to 10 minutes and mix again. the product should achieve the right consistency for application. Finish it by pressing it inside the duct or void and finishing it off with a flat metal or plastic trowel. If the mortar pot starts to harden it is recommended not to add extra water, just remix till it turns back to the desired consistency.

### Curing

48 Hours

### Shelf life

Expiration of **Ressi CFM 920 2K** is 6 months after production date under dry and sheltered conditions

### Packaging

**Ressi CFM 920 2K** is available in the following packaging

2 KG Powder & 500ml Liquid  
20 KG Powder and 5 Ltr Liquid

### Health and safety

**Ressi CFM 920 2K** is not regarded hazardous for transportation. Do not reuse bags or containers and dispose them off as per local rules and regulations. Gloves and suitable masks can be worn during application. Please Refer to the MSDS of the product for further health and safety information.



**RESSICHEM (Pvt.) LIMITED**

Plot # D-83, S.I.T.E., Industrial Area, Manghopir Road, Karachi-75530, Pakistan.  
Tel: +92 213 259 3800-02, Fax: +92 213 259 3803

[www.ressichem.com](http://www.ressichem.com)