

# Technical Data Sheet



**Ressi EPO Gloss Might** is a 2 component epoxy resin based heavy duty, mild chemical resistant, abrasion and impact resistant epoxy floor. It is designed for trowel application in thickness of 300 microns to 4000 microns.

## Uses

**Ressi EPO Gloss Might** gives a tough, high abrasion, chemical and impact resistant topping. It is used either as a coating or a screed for floorings where excellent mechanical properties with superior abrasion and wear characteristics are required. It can be used for industrial floorings, warehouses, workshops, ramps, garages, airport maintenance areas, hospitals, laboratories, metal processing and engineering units and areas subject heavy traffic. It can also be used as a coving or patch repair product.

## Advantages

- ✓ Excellent mechanical properties
- ✓ Can be easily over coated with any epoxy or PU Coating
- ✓ Excellent abrasion resistance and adhesion to concrete surfaces
- ✓ Excellent resistance to impact
- ✓ Easy to apply
- ✓ Early development of initial hardness minimizes down time
- ✓ 3 to 4 times stronger than typical concrete
- ✓ Good bond strength
- ✓ Good Chemical Resistance
- ✓ Unaffected by a wide range of acids, alkalis and industrial chemicals.



**RESSICHEM (Pvt.) LIMITED**

Plot # D-83, S.I.T.E., Industrial Area, Manghopir Road, Karachi-75530, Pakistan.  
Tel: +92 213 259 3800-02, Fax: +92 213 259 3803

[www.ressichem.com](http://www.ressichem.com)

# Technical Data Sheet



## Surface preparation

Surfaces should be free from grease, oil, chemical contamination, dust, laitance, and loose concrete. Appropriate surface preparation equipment such as shot-blast, Scarified or grinder must be used to obtain sound substrate. Surfaces which show any traces of oil must be degreased with a chemical degreaser prior to any surface preparation or grit blasting. Cracks, pinholes, potholes should be repaired with **Ressi EPO Crack Fill**. Uneven concrete should be levelled to produce flat surfaces. New concrete floors must be at least 28 days old prior to application. Moisture content of the concrete or cementitious floors must be less than 5%. Expansion, control & isolation joints should be carried through floors filled with a suitable sealant.

## Priming

Prepared surfaces should be primed using **Ressi EPO Primer**. The primer should be brushed into the substrate using a stiff brush or roller and allowed to become tacky (10-20mins) before the application of Ressi Gloss Might. The primer should be allowed to dry. If the primer has dried, additional coat of the primer should be applied and allowed to become tacky.

## Mixing

Stir the base and hardener components separately. Once both components are mixed, they should be mixed together thoroughly using a slow speed drill attached with paddle for at least 3 minutes (400-600 rpm) until a uniform homogenous mix is achieved.

## Application

Lay **Ressi EPO Gloss Might** over the prepared surface whilst the primer is still tacky. Spread out with a notched trowel to a uniform thickness. Level the material using appropriate trowels and tools to the desired level. Stroke with a steel trowel to achieve a sealed resin rich surface. A Spiked roller can also be used to achieve a uniform surface.

## Limitations

At higher temperatures pot life will be reduced. For working in temperatures below 5°C **Ressi EPO Gloss Might** may need to be put in a hot water bath.



RESSICHEM (Pvt.) LIMITED

Plot # D-83, S.I.T.E., Industrial Area, Manghopir Road, Karachi-75530, Pakistan.  
Tel: +92 213 259 3800-02, Fax: +92 213 259 3803

[www.ressichem.com](http://www.ressichem.com)

# Technical Data Sheet



## Typical properties at 25°C

| Property                | Value                                      |
|-------------------------|--|
| Component               | Two: Part A: Base<br>Part B: Hardener      |
| Mixed Form              | Paste                                      |
| Color request           | Grey and other colors available on request |
| *Mixed Density          | 1.2 Kg/ltr $\pm$ 0.05                      |
| *Setting time           | 3-4 Hours                                  |
| *Full Cure              | 7 Days                                     |
| *Bond Strength          | 2 N / mm <sup>2</sup>                      |
| *Flexural Strength      | 25 N / mm <sup>2</sup>                     |
| *Compressive Strength   | 85 N / mm <sup>2</sup>                     |
| *Tensile Strength       | 15 N / mm <sup>2</sup>                     |
| *Chemical Resistance    | Resistant to mild chemicals                |
| Application temperature | +5°C to +40°C                              |
| Service Temperature     | +5°C to +70°C                              |

\*Typical results under laboratory conditions

## Pack Size

**Ressi EPO Gloss Might** is available in 20 KG Pre packed Kits.

Part A 15 KG      Part B 5 KG



**RESSICHEM (Pvt.) LIMITED**

Plot # D-83, S.I.T.E., Industrial Area, Manghopir Road, Karachi-75530, Pakistan.  
Tel: +92 213 259 3800-02, Fax: +92 213 259 3803

[www.ressichem.com](http://www.ressichem.com)

# Technical Data Sheet



## Coverage

0.25 m<sup>2</sup>/Ltr at 4mm Thickness

## Shelf life

6 Months from date of manufacture when stored under warehouse conditions in original unopened packaging. Extreme temperature / humidity may reduce shelf life.

## Health & Safety

The Packed material if **Ressi EPO Gloss Might** is regarded as non-hazardous for transportation. Once Opened, Extreme temperatures may cause flammability. Do not reuse bags or containers and dispose them off as per local rules and regulations. Gloves and suitable masks can be worn during application. Please Refer to the MSDS of the product for further health and safety information.



**RESSICHEM (Pvt.) LIMITED**

Plot # D-83, S.I.T.E., Industrial Area, Manghopir Road, Karachi-75530, Pakistan.  
Tel: +92 213 259 3800-02, Fax: +92 213 259 3803

[www.ressichem.com](http://www.ressichem.com)