

RESSI EPO ZINC PUTTY

Two-Component Superior Cathodic Protection,
Repair and Rebuilding Compound

10

RESSICHEM[®]
adding life and value to your property

ResSI EPO Zinc Putty 10 is a two-component, solvent-free, high Zinc-filled fast cure epoxy repair compound designed for rebuilding, filling, and repairing galvanized and ferrous metal surfaces. When mixed, the base and hardener react to form a high-strength, sacrificial compound. It is a premium cold galvanizing repair putty that provides excellent cathodic (sacrificial) corrosion protection, strong adhesion, and a metallic zinc appearance. The cured material acts as an effective alternative to hot-dip galvanizing for damaged or worn zinc coatings.

FEATURES & BENEFITS

- ✓ Two-component, easy-to-mix and apply.
- ✓ Excellent adhesion to most rigid substrates.
- ✓ Can be drilled, tapped, machined, or sanded after curing.
- ✓ Resistant to oil, water, fuels, and many industrial chemicals.
- ✓ Ideal for repairing worn parts, cracks, holes, and surface defects.
- ✓ High compressive and tensile strength ensuring durable repairs.

RECOMMENDED USES

- ✓ Repair of zinc castings, galvanized steel surfaces and equipment where a zinc-rich finish and cathodic corrosion protection are required.
- ✓ Rebuilding worn areas of machine parts and metal components.
- ✓ Filling cracks, holes, corrosion pits, and surface irregularities.
- ✓ Suitable for workshops, marine environments, electrical/thermal applications and process industries.

SURFACE PREPARATION

All surfaces must be clean, dry, and free from oil, grease, rust, scale, and contaminants. For best adhesion, the substrate should be roughened by abrasive blasting or mechanical abrasion to achieve a minimum surface profile of 75 microns. After surface preparation, clean thoroughly with a suitable solvent cleaner to remove all dust and residues before applying the compound.

RESSI EPO ZINC PUTTY

Two-Component Superior Cathodic Protection,
Repair and Rebuilding Compound

10

RESSICHEM
adding life and value to your property

APPLICATION

Before use, thoroughly mix the Base and Hardener components in the ratio of 100:33 by weight until a uniform colour and smooth consistency are obtained. The mixed material should be applied immediately using a putty knife, spatula, or trowel.

The working time of the 100gm mixed material is approximately 10 minutes at 25°C, depending on ambient temperature. Machining, drilling, or overcoating may be carried out once the compound has fully cured, typically after 24 hours at 25°C. Clean all tools and application equipment promptly after use with a suitable epoxy thinner or solvent before the material hardens.

SHELF LIFE

12 months from date of manufacture (sealed containers).

RESSI EPO ZINC PUTTY 10

Two-Component Superior Cathodic Protection,
Repair and Rebuilding Compound

RESSICHEM
adding life and value to your property

TECHNICAL PROPERTIES

Property	Typical Data
Type	Two-component (Base + Hardener)
Mixing Ratio (by weight)	100:33
Appearance	Dark Grey Paste
Density	1.64 ± 0.05 g/cm ³ (mixed)
Pot Life	10-12 minutes (100gm) @ 25°C
Touch Dry	45 min – 1.55 hours @ 25°C
Full Cure	24 hours @ 25°C (faster with heat)
Compressive Strength	> 92 MPa
Flexural Strength	> 41 MPa
Temperature Resistance	Up to 90°C (dry service)
Solids	95% or above

RESSI EPO ZINC PUTTY

Two-Component Superior Cathodic Protection,
Repair and Rebuilding Compound

10

RESSICHEM[®]
adding life and value to your property

PACK SIZE

Ressi EPO Zinc Putty 10 is available in the following pack sizes:

250 g and 85 g (Base + Hardener)
500 g and 170 g (Base + Hardener)

HEALTH AND SAFETY

Ressi EPO Zinc Putty 10 contains epoxy resins and amine hardeners. Avoid contact with skin and eyes and do not inhale vapors. Always wear gloves, goggles, and suitable protective clothing during use. Ensure adequate ventilation in the working area. In case of contact, wash immediately with soap and water and seek medical attention if irritation occurs. Refer to the Material Safety Data Sheet (MSDS) for complete safety and handling information.

TECHNICAL DATASHEET RESSI EPO ZINC PUTTY 10