

Ressi EPO Prime – Offshore Mastic

Anticorrosive Epoxy Primer for Cx Extreme Corrosivity Environments



Ressi EPO Prime – Offshore Mastic is a high-performance, two-component anticorrosive epoxy primer specially formulated for Cx corrosivity environments as defined in ISO 12944. Designed for protection of steel structures exposed to extreme humidity, industrial pollution, aggressive marine, or offshore conditions, it provides excellent adhesion, moisture resistance, and long-lasting corrosion protection.

This primer contains active anticorrosive pigments and functional additives that enhance barrier performance and prevent rust formation, even under the most severe environmental conditions. Once cured, it forms a tough, chemically resistant film, providing a strong foundation for intermediate and topcoat layers.

TYPICAL APPLICATION

- ✓ Structural steel frameworks in heavy industrial and offshore installations
- ✓ Storage tanks, pipelines, and chemical plant equipment
- ✓ Marine, offshore, and coastal structures under severe exposure
- ✓ Power plants, refineries, and other high-risk industrial facilities
- ✓ Heavy machinery and industrial equipment
- ✓ General fabrication and maintenance coatings in Cx extreme corrosivity environments

ADVANTAGES

- ✓ Formulated for Cx corrosivity environments (ISO 12944 compliant)
- ✓ Excellent adhesion to properly prepared steel substrates
- ✓ High resistance to extreme humidity, salinity, and industrial pollution
- ✓ Contains active anticorrosive pigments for long-term protection
- ✓ Cures to a tough, chemically resistant film
- ✓ Provides an ideal base for intermediate and topcoat systems
- ✓ Easy to apply by brush, roller, or spray

SURFACE PREPARATION AND MIXING

All surfaces must be clean, dry, and free from oil, grease, rust, mill scale, and other contaminants.

- ✓ For optimal results, abrasive blast cleaning to a minimum of Sa 2½ (ISO 8501-1) is recommended.
- ✓ If blasting is not possible, mechanical cleaning to St 3 standard may be used as an alternative.
- ✓ After cleaning, ensure the surface is free from dust and moisture before primer application.

Ressi EPO Prime – Offshore Mastic

Anticorrosive Epoxy Primer for Cx Extreme Corrosivity Environments



MIXING

Ressi EPO Prime – Offshore Mastic is supplied in pre-measured two-component kits (Base and Hardener).

1. Add the entire contents of the Hardener to the Base.
2. Mix thoroughly using a low-speed mechanical mixer (300–400 rpm) until fully homogeneous.
3. Avoid entrapping air during mixing.

APPLICATION

Apply the mixed material using airless spray, conventional spray, brush, or roller. Ensure uniform film thickness and complete coverage.

- ✓ Recommended Dry Film Thickness (DFT): 200–220 microns per coat (depending on exposure severity)
- ✓ Apply subsequent coats once the primer is dry to touch and within the specified overcoating interval

COVERAGE

Approximately 40–60 sq. ft. per kg per coat @ 200–220 microns, Theoretical coverage values are provided for reference only; actual material consumption may vary depending on surface profile, porosity, and application conditions

LIMITATIONS

When temperatures exceed 35°C working times will be reduced significantly. During application in cold weather correct conditioning is essential. Application should be halted if the ambient or substrate temperature is likely to fall below 10°C.

SHELF LIFE

12 Months from the date of manufacture when stored under warehouse conditions in original unopened packaging. Extreme temperature / Humidity may reduce shelf life.

Ressi EPO Prime – Offshore Mastic

Anticorrosive Epoxy Primer for Cx Extreme
Corrosivity Environments

RESSICHEM[®]
adding life and value to your property

TECHNICAL PROPERTIES

Appearance	Opaque Liquid
Color	Red
Viscosity (Part A)	500 – 1500
Viscosity (Part B)	100 – 150
Mix Ratio (Part A: Part B)	100 : 25
Mix Viscosity @ 25°C / cPs	200 – 400
Mix Density /g / cc	1.22
Working time	90 – 120 minutes
Tack Free Time	4 – 5 Hours
Over coat time	8 Hours – 12 Hours (Depending upon nature of substrate)
Full Cure	7 days
Adhesion Test (ASTM D 3359)	5B (Pass)
Pencil Hardness (ASTM D 3363)	6H (Pass)
Mandrel Test (ASTM D 522)	12mm (Pass)
Impact Resistance Test (ASTM D 2794)	>60 inch-lb

Ressi EPO Prime – Offshore Mastic

Anticorrosive Epoxy Primer for Cx Extreme
Corrosivity Environments



PACK SIZE

Ressi EPO Prime – Offshore Mastic is available in the following pack sizes:

1 KG: Part A 800g
Part B 200g

5 KG: Part A 4 KG
Part B 1 KG

20 KG: Part A 16 KG
Part B 4 KG

HEALTH AND SAFETY

The packed material of **Ressi EPO Prime – Offshore Mastic** is regarded as non-hazardous for transportation. Once opened extreme temperatures may cause the material to be flammable. Do not reuse bags, containers, and packaging materials. It is recommended to dispose the packaging as per local rules and regulations. Gloves and suitable masks can be worn during application. Please refer to MSDS of the product for further health and safety information.