



Crack Heal 930 is a gypsum based quick set joint and crack filler which can easily be used to fill out cracks of various nature up to a thickness of 10mm. **Crack Heal 930** is ideal for the cracks and joints of masonry, plaster, gypsum plaster, gypsum boards and cement boards.

ADVANTAGES

- ✓ For thick and thin layers up to 10mm in a single layer.
- ✓ High filling power.
- ✓ Noncracking and absorption.
- ✓ High stability.
- ✓ Easy to smoothen.
- ✓ Long lasting.
- ✓ Natural and harmless to the environment.
- ✓ Does not contain any carcinogenic material.

TECHNICAL DATA

Appearance	White Powder
Composition	Contains gypsum and selected aggregates along with additives to improve consistency, workability, and durability.
Maximum Aggregate Size	0.3mm
Water application	25% ± 5%
Wet mix life	Approximately 20 Mins (Tested as per BS EN 1015-9)
Compressive strength	4.00 N / mm ² @ 7 days (Tested as per BS EN 1015-11)
Flexural strength	1.00 N / mm ² @ 28 days (Tested as per BS EN 1015-12)
Approximate yield	0.7m ³ / T

*Typical results under laboratory conditions

SURFACE PREPARATION

All loose particles of dust and oil shall be cleaned off the surface prior to application. For very hot climatic conditions, the surface can be dampened with water.

PRODUCT PREPARATION

Crack Heal 930 is a powdered material and simple the addition of water is required for the preparation of this material. It is essential that the water is premeasured with accordance to the amount of material used. The mortar powder should be added over the powder to avoid the settlement of the material at the bottom of the mixing container. Let the mixed material rest for about 2 minutes, after which the application process can begin.



APPLICATION

After the product has achieved the right consistency for application. It can be pressed into the void using the right tools such as a steel blade, trowel, putty knife, or a plastic trowel. It is recommended to use all the mixed material before the mortar starts to harden. **Crack Heal 930** is for internal application only. Application in areas exposed directly to sunlight should be avoided.

CURING

No Curing Required.

SHELF LIFE

Expiration of **Crack Heal 930** is 12 Months after production date under dry and sheltered conditions.

PACKAGING

Crack Heal 930 is available in 2 KG and 20 KG packs.



PRINTED



UNIVERSAL

NOTE:

If printed packaging not available, neutral packaging with label. Lot number and manufacturing date to be stamped at the back of each packaging.