



Patch 365 Plus is a two-component dry premix repairing mortar useful for the repairing of old deformed plaster works, damaged floor screed with potholes and concrete where surface honeycombing has occurred. **Patch 365 Plus** is also highly recommended for the use in refurbishment & renovation works. **Patch 365 Plus** is extremely useful for areas where high strength, water resistivity and some flexibility is required in the mortar.

ADVANTAGES

- ✓ High Strength.
- ✓ Durable.
- ✓ Good workability.
- ✓ Non-Toxic Material.
- ✓ Breathable surface.
- ✓ Water resistant.
- ✓ Environmentally friendly material.
- ✓ Can be left bare or covered.
- ✓ Good Weather resistivity.

SURFACE PREPARATION

All Loose particles dust and oil shall be cleaned off the surface prior to application. For hot climatic conditions, the surface may be dampened with potable water. For restorative plaster works it is recommended to thoroughly remove the old plaster work and expose the base substrate (Block, Brick, or concrete surface) and clean it with potable water to ensure that there are no loose particles on the surface.

PRODUCT PREPARATION

It is important that water and required polymer liquid is premeasured in accordance with the amount of material used. The Mortar powder should be added over the mixed liquid to avoid the settlement of the material at the bottom of the mixing container. The Mixing container should be uncontaminated, non-corrosive and clean. Potable water can also be used for mixing along with the polymer liquid. It is also recommended that the material should be mechanically mixed with a mortar mixer or other mechanical mixing methods to obtain a consistent lump free mix.

APPLICATION

Patch 365 Plus can be applied by hand or wet spray. It should be firmly placed to ensure proper bonding with the prepared surface. A wood flat or plastic float can be used for levelling and initial finish.

TECHNICAL DATA

Component	Two: Part A: Liquid Polymer Part B: Grey Powder
Composition	Contains cement and selected aggregates along with additives to improve consistency, workability, and durability.
Maximum Aggregate Size	1.00 mm
*Wet Mix Life	Approximately 45 minutes @ 20°C (Tested as per BS EN 1015-9)
*Compressive Strength	10.00 N / mm ² @ 28 Days (Tested as per BS EN 1015-11)
*Flexural Strength	2.50 N / mm ² @ 28 Days (Tested as per BS EN 1015-12)
*Approximate Yield	0.63 m ³ / T

*Typical results under laboratory conditions.

CURING

Minimum 48 Hours.

SHELF LIFE

Expiration of **Patch 365 Plus** is at 06 months after production date under dry and sheltered conditions.

PACKAGING

Patch 365 Plus is available in the following packaging.

2.5 KG Kits	Part A: 500ml Liquid Part B: 2 KG Powder
25 KG Kits	Part A: 5 Ltr Liquid Part B: 20 KG Powder

HEALTH AND SAFETY

Patch 365 Plus is regarded as non-hazardous for transportation. Do not reuse bags or containers and dispose them off as per local rules and regulations. Gloves and suitable masks can be worn during application. Please Refer to the MSDS of the product for further health and safety information.