



Ressi TA 230
High Strength Waterproof Tile Adhesive
White

RESSICHEM[®]
adding life and value to your property

Ressi TA 230 White is an extremely versatile tile adhesive for the internal and external applications, swimming pools, basements etc. **Ressi TA 230 White** is highly suitable for the bonding of most types of tiles. **Ressi TA 230 White** is highly suitable for the application of porcelain, marble, granite, ceramic, glass tiles and many other different types of tiles in dry and wet areas. **Ressi TA 230 White** can easily be applied using the application spectrum as defined by BS EN 5385-1.

ADVANTAGES

- ✓ Crack resistant.
- ✓ Non yellowing mortar.
- ✓ Dampness resistant.
- ✓ Longer open time.
- ✓ Salt free mix.
- ✓ Excellent workability.
- ✓ High bond strength.
- ✓ Slip resistant.
- ✓ Longer adjustment time.
- ✓ Waterproof.

SURFACE PREPARATION

All loose particles and oil shall be cleaned off the surface prior to the application. For hot climatic conditions, the surface may be dampened with potable water. Application on most type of cementitious surfaces like block work, concrete and rough plastered surfaces is possible. The surface should be sufficiently aged (At least 7 days for newly erected masonry surface and freshly plastered surface) before the installation of the tiling may begin. It is also recommended that expansion joints should not be tiled over, and suitable treatment should be done over them. Highly absorbent surfaces should be dampened before spreading **Ressi TA 230 White**. Defective and unsound surfaces should be repaired before the installation of the tiles. It is also important to ensure that there is no dust at the backs of the tile, otherwise it may cause hollow sounds and improper adhesion of the tiles to the substrate.

PRODUCT PREPARATION

It is important that water is premeasured in accordance with the amount of material used. The Mortar powder should be added over the water to avoid the settlement of the material at the bottom of the mixing container. The Mixing container should be uncontaminated, non-corrosive and clean. Only potable water should be used for mixing. It is also recommended that the material should be mechanically mixed with a mortar mixer or other mechanical mixing methods to obtain a consistent lump free mix.

ریسیکیم[®]
مضبوطی اور پائیداری کے لئے

📍 D-83,S.I.T.E., INDUSTRIAL AREA, MANGHOPIR ROAD, - 75530, PAKISTAN
☎ +92-309-7772464
☎ +92 21-3259380002
🌐 www.ressichem.com



Ressi TA 230
High Strength Waterproof Tile Adhesive
White

RESSICHEM[®]
adding life and value to your property

APPLICATION

Buttering of the material onto the back of the tiles is usually not recommended as it may cause poor adhesion. Spread the material evenly onto the surface using a suitable straight edge trowel and then notch immediately. To ensure good bonding, it is recommended not to spread the material more than 1m² at a time as the mortar may dry up resulting in poor adhesion and causing difficulties in application. After the application and levelling of the mortar, the tiles should be firmly knocked into the position. Adjustment of the tiles should be done at a maximum of 20 minutes after application.

TECHNICAL DATA

Appearance	White Powder
Composition	Contains cement and selected aggregates along with additives to improve consistency, workability, and durability.
Maximum aggregate size	0.6mm
*Water application	25% ± 5%
*Pull off strength	1.12 N / mm ² @ 28 Days (Tested as per BS EN 1348)
*Slip Test	Non-Slip as per BS EN 1348
*Open time	20 Min Tested as per BS EN 1346
*Water Retention	99.4%
*Application yield / Coverage	0.78m ³ /T

*Typical results under laboratory conditions
These results comply with BS EN 12004 Type C Class 2 E

SHELF LIFE

Expiration of **Ressi TA 230 White** is at 12 months after production date under dry and sheltered conditions.

PACKAGING

Ressi TA 230 White is available in 20 KG Bags.

HEALTH AND SAFETY

Ressi TA 230 White is regarded as non-hazardous for transportation. Do not reuse bags or containers and dispose them off as per local rules and regulations. Gloves and suitable masks can be worn during application. Please refer to the MSDS of the product for further health and safety information.

ریسیکیم
مضبوطی اور پائیداری کے لئے

📍 D-83,S.I.T.E., INDUSTRIAL AREA, MANGHOPIR ROAD, - 75530, PAKISTAN
☎ +92-309-7772464
☎ +92 21-3259380002
🌐 www.ressichem.com