

Zepoxy REH 1958 is a high viscosity aliphatic amine hardener suitable to cure at low temperatures and can also be used as an accelerator for normal temperature curing epoxy systems. **Zepoxy REH 1958** is a reactive accelerator and hence imparts high mechanical properties to the cured systems when compared to systems accelerated with unreactive tertiary amines.

TECHNICAL DATA

Property	Test Method	Result
Appearance	visual	Clear, yellow liquid
*Color	ASTM D 1544-04	8 G max.
*Amine value	ASTM D 1652	350 – 380 mg KOH/g
*Viscosity @ 25°C	ASTM D 2196-05	70,000 – 90,000 cPs
Odor	-	Amine
*AHEW	-	152
*Flash Point	ASTM D 93	>102°C

*Typical results under laboratory conditions.

PACKAGING

Zepoxy REH 1958 is available as follows:

1 KG, 5KG, 15KG, 30KG, and 200KG

HEALTH AND SAFETY

Dispose containers of the materials as per local laws, rules, and regulations. Use gloves, safety masks and other safety apparel as per health and safety laws. For further assistance, please refer to the MSDS of the product for further health and safety information.