

**Zepoxy REH 215X B70** is a 70% solution of a modified aliphatic amine hardener recommended to be used with **Zepoxy RER 011 X75** in protective coatings as an alternate to polyamide-based coatings. This hardener is better performing than standard coating grade polyamide solutions in terms of high gloss, long pot life, excellent flexibility and impact strength and higher yellowing resistance, whereas adhesive strength, corrosion protection and chemical resistance of polyamide solutions is superior.

## TECHNICAL DATA

Property	Test Method	Result
Appearance	visual	Clear to hazy, light green liquid
Color	ASTM D 1544-04	3 G max.
Amine value	ASTM D 1652	125 – 155 mg KOH/g
Viscosity @ 25°C	ASTM D 2196-05	15,000 – 25,000 cPs
Odor	-	Amine
AHEW	-	312
*Flash Point	ASTM D 93	>30°C

\*Typical results under laboratory conditions.

## PACKAGING

**Zepoxy REH 215X B70** is available as follows:

1 KG, 5KG, 15KG, 30KG, and 200KG

## HEALTH AND SAFETY

Dispose containers of the materials as per local laws, rules, and regulations. Use gloves, safety masks and other safety apparel as per health and safety laws. For further assistance, please refer to the MSDS of the product for further health and safety information.