

Zepoxy REH 241, a curing agent based on polyetheramine, is a versatile solution known for its exceptional adhesion, toughness, flexibility, thermal shock resistance, and low color. Additionally, it boasts a prolonged pot life, making it suitable for various applications including epoxy systems, composites, electronics, and construction projects.

TECHNICAL PROPERTIES

| Property | Value | Test Conditions |
|----------------------------------|------------------------|-----------------------------------|
| Density | 0.95 g/cm ³ | |
| Gel Time | >550 min | At 23 °C 100g. Blend |
| Amine Hydrogen Equivalent Weight | 61 g/eq | |
| Boiling Point | >200 °C | |
| Viscosity | 10 mPa-s | At 23 °C. Falling Ball Viscometer |

APPLICATIONS / RECOMMENDED FOR

- Epoxy, Epoxide Resin
- Buildings & constructions
- Electronics / Computers
- Mechanical/ physical performance > Flexibility
- Mechanical/ physical performance > Thermal resistance

PACKAGING

Zepoxy REH 241 is available as follows:

1 KG, 5KG, 15KG, 30KG, and 200KG

HEALTH & SAFETY

Dispose containers of the materials as per local laws, rules, and regulations. Use gloves, safety masks and other safety apparel as per health and safety laws. For further assistance, please refer to the MSDS of the product for further health and safety information.